Acran Boğaziçi Kimya A.Ş. İç Kapı No : 56,57,58 / Bağcılar İstanbul

Mahmutbey Mah. (Istoc Tic. Merk) 2412 Sk. (C Plaza) No.201y thy leng 3HDR 54.090 tr

Technical data sheet High Density Polyethylene BLOW MOULDING Produced in Europe

Refining & Chemicals Polymers

Description

HDPE 51090 is a semi high molecular weight (SHMW) high density polyethylene (HDPE) with high resistance to impact and excellent Environmental Stress Crack Resistance (ESCR). It has been specifically designed for the manufacture of blow moulded articles (jerry-cans) dedicated for the transportation of dangerous goods.

HDPE 51090 is a pellet grade and contains antioxidants.

Characteristics

Property	Method	Unit	Typical value (*)
Density	ISO 1183	g/cm³	0.950
Melt Flow Rate (190°C/21.6 kg)	ISO 1133/G	g/10 min	7
FNCT	ISO 16770	h	27
Notched Charpy Impact Resistance –30°C	ISO 179-1	kJ/m²	20

(*) Data not intended for specification purposes

Processing

It is recommended to process HDPE 51090 within the temperature range 180-220°C.

Handling and storage

Please refer to the safety data sheet (SDS) for handling and storage information. It is advisable to convert the product within one year after delivery provided storage conditions are used as given in the SDS of our product. SDS may be obtained from the website: www.totalrefiningchemicals.com

Information contained in this publication is true and accurate at the time of publication and to the best of our knowledge. The nominal values stated herein are obtained using laboratory test specimens. Before using one of the products mentioned herein, customers and other users should take all care in determining the suitability of such product for the intended use. Unless specifically indicated, the products mentioned herein are not suitable for applications in the pharmaceutical or medical sector. The Companies within Total Petrochemicals do not accept any liability whatsoever arising from the use of this information or the use, application or processing of any product described herein. No information contained in this publication can be considered as a suggestion to infringe patents. The Companies disclaim any liability that may be claimed for infringement or alleged infringement of patents.