

# SABIC® PS 330

## HIGH IMPACT POLYSTYRENE FOR SHEET EXTRUSION

### DESCRIPTION

PS 330 is high Impact Polystyrene manufactured by continuous mass polymerization of styrene monomer. An elastomer is incorporated during polymerization to achieve impact resistance property. It is generally opaque in color. It is a high impact strength polystyrene with high heat deflection temperature and good physical properties.

### TYPICAL APPLICATIONS

PS 330 is primarily designed for extrusion and thermoforming applications. It can be used for food packaging and dairy products.

### TYPICAL PROPERTY VALUES

Revision 20221103

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>PHYSICAL</b>			
Melt Flow Rate, 230°C/2.16 kgf <sup>(1)</sup>	4	g/10 min	ASTM D1238
<b>POLYMER PROPERTIES</b>			
Load Density@ 23°C	1040	kg/m <sup>3</sup>	ASTM D792
Bulk Density (Method B)	600	kg/m <sup>3</sup>	ASTM D1895
<b>MECHANICAL PROPERTIES</b>			
Tensile Strength	29	MPa	ASTM D638
Tensile Elongation	50	%	ASTM D638
Tensile modulus	2353	MPa	ASTM D638
Flexural Strength	44	MPa	ASTM D790
Flexural Modulus	2647	MPa	ASTM D790
Izod impact notched at 23 °C	110	J/m	ASTM D256A
Rockwell Hardness, L-Scale <sup>(2)</sup>	67	-	ASTM D785
M-Scale	10	-	ASTM D785
<b>THERMAL PROPERTIES</b>			
<b>Flammability Rating, UL 94</b>			
@ 1.3 mm and 3 mm (natural color)	HB	Class	-
Vicat Softening Point, (Rate A/50°C)	99	°C	ASTM D1525
Heat Deflection Temperature (Method B, 455 KPa, Annealed)	97	°C	ASTM D648

(1) Typical values; not to be construed as specification limits.

(2) Based on injection molded specimens.

### PROCESSING CONDITIONS

Typical extruder barrel temperature (°C) profile for PS 330: 185-205, Die temperature (°C) : 215

### STORAGE AND HANDLING

PS 330 is suitable for Food contact application. Detailed information is provided in relevant Material Safety Datasheet and for additional specific information please contact SABIC local representative for certificate.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.