

## Typical value for Solarene<sup>®</sup>

### Grade : Solarene<sup>®</sup> HIPS, H-724

Test items	Unit	Test Method	Test Condition	Typical Value
<b>Mechanical Properties</b>				
Tensile Stress at yield	kgf/cm <sup>2</sup> [MPa]	ASTM D 638	-	250 [25]
Elongation	%	ASTM D 638	-	70
Flexural Strength	kgf/cm <sup>2</sup> [MPa]	ASTM D 790	-	420 [41]
Flexural Modulus	kgf/cm <sup>2</sup> [MPa]	ASTM D 790	-	21,000 [2,059]
IZOD Impact Strength	kgf·cm/cm [J/m]	ASTM D 256	3.2mm Notched	13.5 [132.4]
Rockwell Hardness	-	ASTM D 785	L-Scale	60
<b>Rheological Properties</b>				
Melt Flow Index	g/10 min	ASTM D 1238	200°C/5kg	5.0
<b>Thermal Properties</b>				
Vicat Softening Temp.	°C	ASTM D 1525	A/50	96
Mold Shrinkage	%	ASTM D 955	-	0.4~0.7
<b>Physical Properties</b>				
Specific Gravity	-	ASTM D 792	-	1.04
Water Absorption	%	ASTM D 570	-	0.03
<b>Burning Properties</b>				
Flammability	class	UL 94	-	HB

\* The above values are only the representatives of natural color specimen.

\* The listed values should be used for referential purposed only.