



LDF2926SB

Low Density Polyethylene

PRODUCT DESCRIPTION

This type of LDPE is a homopolymer of ethylene produced by an autoclave process. This reference contains slip and antiblock additives.

PROCESSING METHODS

Blown Film Extrusion

CHARACTERISTICS

Good Openability
 Low COF
 Easy Procesability

APPLICATIONS

Thin Bags for Consumer Packaging
 Rolls for Automatic Food Packaging

RESIN PROPERTIES

Melt Flow Rate 2.16 kgf/190 °C MFR₂
Density 23 °C
Slip
Antiblock
Antioxidant Package

TEST METHOD

ASTM D1238
 ASTM D1505

VALUES, English Units

2.0 g/10 min
 0.926 g/cm³
 750 ppm
 2,750 ppm
 Yes

VALUES, International Units

2.0 g/10 min
 0.926 g/cm³
 750 ppm
 2,750 ppm
 Yes

BLOWN FILM PROPERTIES

Evaluated Film Thickness
Dart Impact Strenght
 38.0 mm (1.5 in), 0.66 m (26.0 in), F50

TEST METHOD

 ASTM D1709A

VALUES, English Units

1.25 mils
 65 g

VALUES, International Units

31.8 µm
 65 g

Elmendorf Tear Strenght

ASTM D1922

MD 240 g
 TD 230 g

240 g
 230 g

Tensile Strenght at Break

ASTM D882

MD 3,335 psi
 TD 2,900 psi

23.0 MPa
 20.0 MPa

20,0 in/min (508 mm/min)

Tensile Elongation at Break

ASTM D882

MD 330 %
 TD 560 %

330 %
 560 %

20,0 in/min (508 mm/min)

Haze

ASTM D1003

7.0 %

7.0 %

Specular Gloss 60°

ASTM D2457

110.0

110.0

PROCESSING CONDITIONS OF EVALUATED FILM

Die Diameter
 Die Gap
 Melt Temperature
 Blow-up Ratio, BUR
 Output

VALUES, English Units

8.0 pulgadas
 38 mils
 400 °F
 2.5 ---
 250.0 Lb/h

VALUES, International Units

203 mm
 1.0 mm
 204 °C
 2.5 ---
 113.4 kg/h

The data presented here is true and accurate to the best of our knowledge. Likewise, the values are nominal and should not be taken as minimum or maximum specifications. No warranty, express or implied, is made regarding resin performance. The customer must validate these properties according to his own evaluations on his machine and in his laboratory.

REGULATORY COMPLIANCE

This resin complies with the following FDA regulation: 21 CFR 177.1520: Olefinic Polymers. This regulation describes polyolefin resins that can be used safely for food packaging and preservation at low temperatures and at ambient temperatures. This resin is not designed for use in medical applications and should not be used in such applications.