



Luban HS-7028- U

Linear Low Density Polyethylene

Description

Luban HS-7028-U is a hexene LLDPE grade offering excellent drawdown and puncture resistance combined with high gloss and clarity. Films made with Luban HS-7028-U have very good tensile and toughness properties.

Additives:

- Thermal Stabilizer

Application

Lamination film, stretch wrap film, cling film, agricultural Film, bag in box, food packaging films, FFS packaging films, liner bags, multi-layer packaging films

Properties (Typical Values)

Property	Unit	Test method	Value*
Melt Index (190°C/2.16 kg)	g/10 min	ASTM D1238	1
Density	g /cm ³	ASTM D792	0.918
Peak melting temperature	°C	Univation Method	120
Tensile stress at break (MD/TD)	MPa	ASTM D882	57/38
Elongation at break (MD/TD)	%	ASTM D882	590/860
Secant modulus – 1% secant (MD/TD)	MPa	ASTM D882	220/250
Dart Drop Impact	g	ASTM 1709A	120
Elmendorf tear strength (MD/TD)	g	ASTM D1922	120/480
Gloss (45°)		ASTM D2457	47
Haze	%	ASTM D1003	9

*The film properties have been measured on 30 µm (1.18 mil) thick films (Blow-up ratio: 2.5).

Note: These are typical properties only and are not to be construed as specifications. Users should confirm results by their own tests.



Luban HS-7028- U Linear Low Density Polyethylene

Storage and Handling

Luban HS-7028- U should be stored in well ventilate area during handling or processing of to prevent accumulation of dust and fumes. Avoid contact with strong oxidizers, excessive heat, sparks or open flame as this could well speed up alteration and consequently loss of quality of the material in which could lead to unforeseen dangers. The bags must be protected from direct sunlight and should be stored in shaded and completely dry area for good processing.

Safety

Luban HS-7028- U is not classified as dangerous preparation. For further information about safety in handling and processing please refer to the Safety Data Sheet.

Food Contact

Luban HS-7028- U meets the requirements of the U.S. Food and Drug Administration (FDA) as specified in 21 CFR 177.1520, covering safe use of polyolefin articles and components of articles intended for direct food contact. For additional information on approved conditions of use for food contact applications, please refer to the "Product Stewardship Declaration".

Recycling

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

Updated: Mar. 2020

Disclaimer:

Values given here are typical and should not be interpreted as specification. Before using OQ product, customers and other users should make their own independent determination that the product is suitable for the intended use. This document does not constitute a warranty, express or implied, including a warranty of merchantability or fitness for a particular purpose. In addition, no immunity under OQ or third parties' intellectual property rights shall be implied from this document. No one is authorized to make any warranties, issue any immunities or assume any liabilities on behalf of OQ except in a writing signed by an authorized OQ employee. Unless otherwise agreed in writing, the exclusive remedy for all claims is replacement of the product or refund of the purchase price at OQ's option, and in no event shall OQ be liable for special, consequential, incidental, punitive or exemplary damages.