

# SIBUR

## Technical Data Sheet

### PE LL09200 NP

#### Linear Low-Density Polyethylene

#### PRODUCT DESCRIPTION

LL09200 NP is a butene linear low-density polyethylene. Films produced from this resin show excellent puncture resistance, high tensile strength and good sealing performance.

#### TYPICAL APPLICATIONS

LL09200 NP is recommended for the production of heavy duty sacks, agricultural films, liners, carrier bags, frozen food bags, lamination and coextruded films and industrial packaging. It is suitable for blending with other polyethylene resins, such as LDPE or HDPE resins.

Properties	Conditions	Method	Typical values*	Units
Resin properties				
Melt Flow Rate	190 °C/2.16 kg	ISO 1133-1	0.9	g/10 min
Density		ISO 1183	0.920	g/cm <sup>3</sup>
Properties measured on 38 µm film**				
Tensile Strength at Break	MD	ISO 527-1	39	MPa
Elongation at Break	MD	ISO 527-1	530	%
Tensile Stress at Yield	MD	ISO 527-1	9	MPa
Tear Strength	MD/TD	ASTM D1922	130/260	g/25 µm
Dart Drop Impact Strength		ASTM 1709	120	g
Thermal				
Vicat Softening Temperature	10 N	ISO 306	98	°C

\*The values given are typical values measured on the product. These values should not be considered as specification.

\*\*Properties were measured on film extruded at a blow up ratio 2:1 with a melt temperature of 225 °C.

#### REACH Statement

Polymers are exempt of REACH registration. However, their raw materials which mean monomers and relevant additives have been registered.

**PJSC «Sibur Holding» (and its subsidiaries)** is committed to fully respect REACH legislation and to use only REACH compliant raw materials.