



**()** 0 (212) **659 94 37 (2)** 0 (212) **659 94 38** 

● www.**acran**.com.tr ≥ info@**acran**.com.tr

# Westlake Chemical



Linear Low Density Polyethylene

## Application/Uses

- Stretch wrap
- Agricultural films
- Trash bags
- Co-extruded structures

#### **Product Description**

Westlake LF9120CC is a butene LLDPE with excellent mechanical and downgauging advantages. It is suitable for can liners, stretch wrap, agricultural film, and blending with LDPE. This Kosher compliant product is formulated with 1000 ppm slip and 5500 ppm anti-block.

Typical Physical Properties			
<u>Property</u>		Test Method	Typical Value, Units
Melt Index Density (formulated) Haze (formulated) Dart Impact Tensile Break Ultimate Elongation 1% Secant Modulus	MD TD MD TD MD	D 1238 D 1505 D 1003 D 1709 D 882 D 882 D 882 D 882 D 882 D 882 D 882 D 882 D 882	1.1 g/10 min 922 kg/m <sup>3</sup> (0.922 g/cm <sup>3</sup> ) 22.0 % 120 g/mil 5,200 psi 3,600 psi 670% 900% 27,000 psi
	TD	D 882	30,000 psi

<sup>a</sup> Unless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

<sup>b</sup> Unless noted otherwise, the test method is ASTM.

<sup>c</sup> Units are in SI or US customary units.

## NOTES

Kosher Compliant. Test specimens for blown film: nominal thickness 1.0 mils fabricated at 2.5:1 BUR.

## FDA

This product has some 21 CFR clearances. Please contact Westlake Product Regulatory Department for statements.

## PROCESSING

Blown film melt temperatures of 400° F – 420° F are recommended for Westlake Chemical LF9120CC.

#### COMMENTS

Properties reported here are based on limited testing. Westlake makes no representation that the material in any particular shipment will conform exactly to the values given.

Westlake and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.

WESTLAKE CHEMICAL CORPORATION 2801 Post Oak Blvd Suite 600 Houston, Texas

Customer Service: 1-800-545-9577