



Formosa Industries

Formolene® LJ2650B

Linear Low-Density Polyethylene (LLDPE) Resin for Injection Molding

Formolene® LJ2650B is a butene based LLDPE resin designed for injection molded application such as housewares, containers and lids. Formolene® LJ2650B offers excellent flow and stiffness-toughness balance ideally recommended for applications requiring physical performance and enhanced processability.

Formolene® LJ2650B meets all requirements of the U.S. Food and Drug Administration as specified in 21 CFR 177.1520, covering safe use of polyolefin articles intended for direct food contact.

Suggested Applications:

Caps & Closures

Containers

Housewares

Lids

Outdoor and Power Tools

Additives:

Antioxidant - Yes

Nominal Values

PROPERTY*	ASTM TEST METHOD	ENGLISH		SI	
		Unit	Value	Unit	Value
Density	D1505	g/cc	0.926	g/cc	0.926
Melt Index, (190°C/2.16kg)	D1238	g/10 min.	50.0	g/10 min.	50.0
Tensile Strength					
Yield	D638	psi.	1800	MPa	12.4
Break	D638	psi.	1100	MPa	7.6
Tensile Elongation					
Yield	D638	%	12	%	12
Flexural Modulus – 2% Secant	D790B	psi.	61000	MPa	421
Durometer Hardness (Shore D)	D2240	-	56	-	56
Deflection Temperature Under Load (66 psi)	D648	°F	126	°C	52
Vicat Softening Temperature	D1525	°F	194	°C	90

Note: All properties were derived from compression molded specimens. Actual properties may vary depending on operating conditions and additive packages. Properties are not intended to be used as specifications.

Published 05/26/2023

Any inquiries regarding this data sheet should be addressed to: 9 Peach Tree Hill Road • Livingston, NJ 07039 • Phone: (800) 363-1823 • Fax: (973) 716-7483

The information and recommendations in this publication are, to the best of our knowledge, reliable. Suggestions concerning uses or applications are only the opinion of FORMOSA INDUSTRIES CORPORATION and users should perform their own tests to determine the suitability of these products for their own particular purposes. However, because of numerous factors affecting the results, FORMOSA INDUSTRIES CORPORATION MAKES NO WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING THOSE OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, other than that the material conforms to the applicable current Standard Specifications Statement herein, therefore, should not be construed as representations or warranties. Statements concerning the use of the products of formulations described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is assumed.

Formolene® is a registered trademark of Formosa Plastics Corporation, U.S.A. Formosa Industries Corporation is an authorized user of this trademark.