

0 (212) 659 94 38

🧕 info@acran.com.tr

## Supreme<sup>™</sup> 021S

Supreme<sup>™</sup> 021S, metallocene POP, is an ethylene-octene copolymer that performs well in a wide range of general purpose of POP blown film applications, and has excellent melt flow characteristics.

Applications: Low-temperature Seal Packaging, Lamination Film, Impact Modification, etc.

Additives	Antiblock: Yes	Slip: Yes			
			Typical Values	Unit	Test Method
Resin	Co-monomer		Octene-1		SK Method
Properties	Density		0.902	g/cm <sup>3</sup>	ASTM D1505
	МІ		1.0	g/10min	ASTM D1238
	Melting Point		~ 100	°C	SK Method
Film	Dart Drop Impact		> 1000	g	ASTM D1709
<b>Properties*</b>	Haze		5	%	ASTM D1003
	Lowest Heat-seal Temp.		80	°C	SK Method
	Initial Tear Strength	MD	75	kg/cm	ASTM D1004
		TD	90	kg/cm	ASTM D1004
	Elmendorf Tear Strength	MD	10	g/um	ASTM D1922
		TD	17	g/um	ASTM D1922
	Tensile Strength at Break	K MD	480	kg/cm <sup>2</sup>	ASTM D882
		TD	425	kg/cm <sup>2</sup>	ASTM D882
	Elongation at Break	MD	600	%	ASTM D882
		TD	620	%	ASTM D882
	Secant Modulus (1%)	MD	695	kg/cm <sup>2</sup>	ASTM D882
		TD	780	kg/cm <sup>2</sup>	ASTM D882

## Conditions for blown film production

- Machine: Macci blown film line with 50Ø screw

- Film specification: 50um x 600mm

These are typical values and are not to be construed as specifications. The physical properties are highly dependent on the manufacturing conditions. So customers should confirm performances by their own tests.