

 Acran Boğaziçi Kimya A.Ş.

 Mahmutbey Mah. (İstoç Tic. Merk) 2412 Sk. (C Plaza) No:2

 İç Kapı No : 56,57,58 / Bağcılar İstanbul

 ♥ 0 (212) 659 94 37
 ● www.acran.com.tr

 ● 0 (212) 659 94 38
 ⊠ info@acran.com.tr



SABIC® PP 80EK20S Provisional

PP block copolymer for Sheet extrusion

Description:

SABIC® PP 80EK20S is a nucleated impact copolymer developed for extrusion applications. It is typically used for extrusion of sheets, profiles and corrugated boards.

Health, Safety and Food Contact regulations:

Material Safety Data Sheets (MSDS) and Product Safety declarations are available on our Internet site http://www.SABIC-europe.com

The product mentioned herein is in particular not tested and therefore not validated for use in pharmaceutical/ medical applications.

Typical values				Revision 201407
Properties		Unit (Si)	Values	Test methods
Polymer properties				
Melt flow rate (MFR) at 230 °C and 2.16 kg Density		dg/min kg/m³	0.8	ISO 1133
Formulation		Kg/III	303	
Anti static agent		-	No	-
Nucleating agent		-	Yes	-
Mechanical properties				
Tensile test				ISO 527-2 1A
stress at yield	1)	MPa	20	
strain at yield	1)	%	5	
tensile modulus	2)	MPa	1300	
Izod impact notched				ISO 180/1A
at 23 °C		kJ/m²	No Break	
at 0 °C		kJ/m²	No Break	
Charpy impact notched				ISO 179/1eA
at 23 °C		kJ/m²	80	
at 0 °C		kJ/m²	60	
Hardness Shore D		-	63	ISO 868

Speed of testing: 50 mm/min
 Speed of testing: 1 mm/min

. .





Acran Boğaziçi Kimya A.Ş. Mahmutbey Mah. (İstoç Tic. Merk) 2412 Sk. (C Plaza) No:2 İç Kapı No : 56,57,58 / Bağcılar İstanbul



SABIC® PP 80EK20S Provisional

PP block copolymer for Sheet extrusion

Quality:

SABIC Europe is fully certified in accordance with the internationally accepted quality standard ISO9001.

Storage and handling:

Avoid prolonged storage in open sunlight, high temperatures (<50 °C) and /or high humidity as this could well speed up alteration and consequently loss of quality of the material and /or its packaging. Keep material completely dry for good processing.

Disclaimer. The information contained herein may include typical properties of our products or their typical performances when used in certain typical applications. Actual properties of our products, in particular when used in conjunction with any third party material(s) or for any non-typical applications, may differ from typical properties.

It is the customer's responsibility to inspect and test our product(s) in order to satisfy itself as to the suitability of the product(s) for its and its customers particular purposes. The customer is responsible for the appropriate, safe and legal use, processing and handling of all product(s) purchased from us.

Nothing herein is intended to be nor shall it constitute a warranty whatsoever, in particular, warranty of merchantability or fitness for a particular purpose.

SABIC Europe as referred to herein means any legal entity belonging to the SABIC Europe group of companies.