

Technical Data Sheet

Sahara C 440 HT

Polypropylene, Impact Copolymer

Sahara C 440 HT is a nucleated heterophasic copolymer with antistatic agent used injection moulding applications. It combines a good impact/stiffness balance with a high fluidity.

Sahara C 440 HT is typically used by customers in opaque containers, housewares, toys and in thin-walled containers for food packaging (e.g. margarine tubs, yoghurt pots, etc.).

Product Characteristics:

Status	:	Commercial:Active
Processing Method	:	Injection Molding
Application	:	Housewares, Opaque Containers, Sports, Leisure and Toy
Market	:	Consumer Products; Rigid Packaging
Attribute	:	Contains Antistat; High Flow; Impact Copolymer; Nucleated.

Typical Properties	Test Method	Nominal Value	Unit
Physical			
Density	ISO 1183-1	0.9	g/cm ³
Melt flow rate (230°C/2.16kg)	ISO 1133-1	44	g/10 min
Mechanical			
Tensile Modulus	ISO 527-1, -2	1550	MPa
Tensile Stress at Yield	ISO 527-1, -2	28	MPa
Tensile Strain at Break	ISO 527-1, -2	30	%
Tensile Strain at Yield	ISO 527-1, -2	5	%
Impact			
Charpy Impact Strength - Notched (23 °C, Type 1, Edgewise, Notch A) (0 °C, Type 1, Edgewise, Notch A) (-20 °C, Type 1, Edgewise, Notch A)	ISO 179	5	kJ/m ²
	ISO 179	3.5	kJ/m ²
	ISO 179	3	kJ/m ²
Ductile/Brittle transition temperature	ISO 6603-2	-53	°C
Thermal			
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	ISO 75B-1, -2	95	°C
Vicat softening temperature (A/50 N)	ISO 306	151	°C

Notes:

Typical properties; not to be construed as specifications.

Users should review the applicable Material Safety Data Sheet before handling the product.

Before using a product sold Sahara Marketing Company, users should make their own independent determination that the product is suitable for the intended use and can be used safely and legally. SELLER MAKES NO WARRANTY; express or implied (including any warranty of merchantability or fitness for a particular purpose or any warranty) other than as separately agreed to by the parties in a contract.

This product(s) may not be used in:

- any U.S. FDA Class I, Health Canada Class I, and/or European Union Class I medical devices, without prior notification to Seller for each specific product and application; or
- the manufacture of any of the following, without prior written approval by Seller for each specific product and application: U.S. FDA Class II Medical Devices; Health Canada Class II or Class III Medical Devices; European Union Class II Medical Devices; film, overwrap and/or product packaging that is considered a part or component of one of the aforementioned medical devices; packaging in direct contact with a pharmaceutical active ingredient and/or dosage form that is intended for inhalation, injection, intravenous, nasal, ophthalmic (eye), digestive, or topical (skin) administration; and tobacco related products and applications.

Additionally, the product(s) may not be used in:

- U.S. FDA Class III Medical Devices; Health Canada Class IV Medical Devices; European Class III Medical Devices;
- applications involving permanent implantation into the body;
- life-sustaining medical applications; and (iv) lead, asbestos or MTBE related applications. All references to U.S. FDA, Health Canada, and European Union regulations include another country's equivalent regulatory classification.

Processing Techniques:

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Health and Safety:

The resin is manufactured to the highest standards, but special requirements apply to certain applications such as food end-use contact and direct medical use. For specific information on regulatory compliance contact your local representative.

Workers should be protected from the possibility of skin or eye contact with molten polymer. Safety glasses are suggested as a minimal precaution to prevent mechanical or thermal injury to the eyes.

Molten polymer may be degraded if it is exposed to air during any of the processing and off- line operations. The products of degradation may have an unpleasant odor. In higher concentrations they may cause irritation of the mucus membranes. Fabrication areas should be ventilated to carry away fumes or vapors. Legislation on the control of emissions and pollution prevention should be observed.

The resin will burn when supplied with excess heat and oxygen. It should be handled and stored away from contact with direct flames and/or ignition sources. While burning, the resin contributes high heat and may generate a dense black smoke.

Recycled resins may have previously been used as packaging for, or may have otherwise been in contact with, hazardous goods. Converters are responsible for taking all necessary precautions to ensure that recycled resins are safe for continued use.

For further information about safety in handling and processing please refer to the Safety Data Sheet.

Conveying:

Conveying equipment should be designed to prevent production and accumulation of fines and dust particles that are contained in polymer resins. These particles can under certain conditions pose an explosion hazard. Conveying systems should be grounded, equipped with adequate filters and regularly inspected for leaks

Storage:

The resin is packed in 25 kg bags, octabins or bulk containers protecting it from contamination. If it is stored under certain conditions, i.e. if there are large fluctuations in ambient temperature and the atmospheric humidity is high, moisture may condense inside the packaging. Under these circumstances, it is recommended to dry the resin before use. Unfavorable storage conditions may also intensify the resin's slight characteristic odor.

Resin should be protected from direct sunlight, temperatures above 40°C and high atmospheric humidity during storage. Higher storage temperatures may reduce the storage time.

The information submitted is based on our current knowledge and experience. In view of the many factors that may affect processing and application, these data do not relieve processors of the responsibility of carrying out their own tests and experiments; neither do they imply any legally binding assurance of certain properties or of suitability for a specific purpose. This information does not remove the obligation of the customer to inspect the material on arrival and notify us of any faults immediately. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and legislation are observed.

Compliance & Product Stewardship Department

Contact Details:

Website: www.sipchem.com

Email: marketing@sipchem.com

Phone: +966 13 359 3372

Disclaimer

Before using the product listed above, customers and other users should take care in determining the suitability of such product for the intended use. SIPCHEM do not accept any liability whatsoever arising from the use of this information or the use, application or processing of any product described herein.