

HSPB Block Copolmer Injection Grade  
**YUHWA POLYPRO SB9310**

### Description

- Application : Injection
- Features : High Impact Strength, Good Compatibility with Filler and Rubber
- Uses : Battery Case, Electric Appliances and Grocery, PP Compound Base Resin

### Properties

Item	Value	Unit	Test Method
Melt Index	10	g/10min.	ASTM D1238
Density	0.91	g/cm <sup>3</sup>	ASTM D1505
Mold Shrinkage	1.4~1.8	%	KPIC Method
Tensile Strength at Yield	270	kg <sub>f</sub> /cm <sup>2</sup>	ASTM D638
Elongation at Break	>500	%	ASTM D638
Flexural Modulus	12,500	kg <sub>f</sub> /cm <sup>2</sup>	ASTM D790
Hardness (Rockwell)	90	R Scale	ASTM D785
Impact Strength (Izod with Notch) 25°C	22	kg <sub>f</sub> cm/cm	ASTM D256
Impact Strength (Izod with Notch) -20°C	4.5	kg <sub>f</sub> cm/cm	ASTM D256
Melting Point	165	°C	ASTM D3418
Softening Point (Vicat)	152	°C	ASTM D1525
Heat Deflection Temperature	122	°C	ASTM D648

- Above data are intended to serve as guides only, and are not sales specification limits.

### Contact Info

14 Nov.2014

International Trade  
TEL: 82-2-3706-0841~0849 FAX: 82-2-3706-0893~0894 e-mail: trade@kpicc.com

Technical Service  
TEL: 82-80-010-1515, 82-2-2122-1532~1538 FAX: 82-2-2122-1519 e-mail: H15106@kpic.co.kr