

LOTTE CHEMICAL

January, 2013

KOPELEN JH-350

PP BLOCK COPOLYMER

General Information

Description

JH-350 is high impact block copolymer with high ethylene content as co-monomer. This grade is designed to be processed in conventional Injection molding equipment and base resin for compounding.

JH-350 shows extremely high impact resistance at low temperature and has also high strength.

Applications

- ◆ General articles
- ◆ Automotive compound base resin

Physical Properties¹

| Physical | Test Method | Nominal Values | | | |
|---|-------------|----------------|---------------------|-------|-----|
| Melt Flow Index | ASTM D1238 | 10 | g/10min | | |
| Density | ASTM D792 | 0.9 | g/cm ³ | | |
| Mechanical | | | | | |
| Tensile Stress (Yield) | ASTM D638 | 230 | kgf/cm ² | 23 | MPa |
| Tensile Strain (Break) | ASTM D638 | >100 | % | >100 | % |
| Flexural Modulus | ASTM D790 | 11,000 | kgf/cm ² | 1,080 | MPa |
| Impact | | | | | |
| Notched Izod Impact Strength (23 °C) | ASTM D256 | 12.0 | kgf-cm/cm | 118 | J/m |
| Notched Izod Impact Strength (-10 °C) | ASTM D256 | 5.5 | kgf-cm/cm | 54 | J/m |
| Thermal | | | | | |
| Heat Deflection Temperature (4.6kgf/cm ²) | ASTM D648 | 100 | °C | | |
| Additional Properties | | | | | |
| Flammability | UL94 | HB | | | |

NOTE

ISO 9001, 14001, /ITS 16949

¹ Physical Properties : these are not to be construed as specifications

LOTTE CHEMICAL

January, 2013

KOPELEN JH-350

PP BLOCK COPOLYMER

General Information

Description

JH-350 is high impact block copolymer with high ethylene content as co-monomer. This grade is designed to be processed in conventional Injection molding equipment and base resin for compounding. JH-350 shows extremely high impact resistance at low temperature and has also high strength.

Applications

- General articles
- Automotive compound base resin

Physical Properties¹

| Physical | Test Method | Nominal Values | | | |
|---|-------------|----------------|---------------------|------|-----|
| Melt Flow Index | ISO 1133 | 10 | g/10min | | |
| Density | ISO 1183 | 0.9 | g/cm ³ | | |
| Mechanical | | | | | |
| Tensile Stress (Yield) | ISO 527-1 | 220 | kgf/cm ² | 22 | MPa |
| Tensile Strain (Break) | ISO 527-1 | >100 | % | >100 | % |
| Flexural Modulus | ISO 178 | 9,000 | kgf/cm ² | 880 | MPa |
| Impact | | | | | |
| Notched Izod Impact Strength (23 °C) | ISO 180 | 11 | kgf-cm/cm | 105 | J/m |
| Notched Izod Impact Strength (-10 °C) | ISO 180 | 5 | kgf-cm/cm | 49 | J/m |
| Thermal | | | | | |
| Heat Deflection Temperature (4.6kgf/cm ²) | ISO 75-1 | 80 | °C | | |
| Additional Properties | | | | | |
| Flammability | UL94 | HB | | | |

NOTE

ISO 9001, 14001, /ITS 16949

¹ Physical Properties : these are not to be construed as specifications