

Technical Data Sheet

EGYPELENE® FM525J

Polypropylene, Homopolymer

Product Description

EGYPELENE® FM525J is a polypropylene homopolymer suitable for production of biaxially oriented polypropylene films (BOPP). The product is suitable for metallizable film, both as monolayer and in coextruded structures. It contains a standard processing stabilization but does not contain any slip, anti-blocking agents and no Calcium Stearate. EGYPELENE™ FM525J offers good optical, easy processing and very good film profile.

Product Characteristics

Processing Methods

BOPP, Thermoforming

Features

Good transparency, Good gloss, High stiffness, Good optical properties Calcium stearate free, Phthalate free, Reactor grade, Good processability and Good color stability

Typical Customer Applications

Thermoformed Food Containers Food packaging: biscuits, chocolates, chips, baked foods, pasta, snack foods, pet foods etc.
Non-food packaging: soaps, detergents and textile bags.

Typical Properties	Normal Value	Units	Test Methods
Physical			
Melt flow	3	g/10 min	ISO 1133
Density	0.9	g/cc	ISO 1183
Mechanical			
Flexural Modulus	1350	Mpa	ISO 178
Tensile Stress at Break, (23 °C, 50mm/min)	20	Mpa	ISO 527
Tensile Stress at Yield, (23 °C, 50mm/min)	32	Mpa	ISO 527
Tensile Strain at Yield, (23 °C, 50mm/min)	10	%	ISO 527
Thermal			
Vicat Softening Temperature	153	°C	ISO 306

Regulatory Information

Egyptian Propylene & Polypropylene certify that the above product is in compliance with the USA FDA code of Federal Regulations (CFR 21) section 177.1520 (C) 1.1 and is suitable for use in articles that contact food also is in compliance with the EU Regulation 10/2011 as amended.

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally. In addition to any prohibitions of use specifically noted in this document, EPP may further prohibit or restrict the sale of its products into certain applications. For further information, please contact Egyptian Propylene & Polypropylene at info@ep-eg.com