

HB 4500 GP

Technical Data Sheet
Polypropylene, Homopolymer



Product Description

HB 4500 GP is a homopolymer polypropylene usually used by customers for thin walled injection moulding application. It exhibits a high fluidity combined with a good stiffness.

HB 4500 GP is non-phthalate grade. This product is suitable for food contact.

Product Characteristics

Application	General Purpose. Furniture. Housewares
Processing Method	Compounding. Injection Molding. TWIM
Market	Consumer Products
Features	High Flow. Medium Stiffness. Homopolymer Phthalate-Free

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate (230°C/2.16kg)	45	g/10 min	ISO 1133
Mechanical			
Flexural modulus (2 mm/min)	1450	MPa	ISO 178
Tensile modulus (1 mm/min)	1400	MPa	ISO 527
Tensile Strength at Yield (50 mm/min)	32	MPa	ISO 527
Elongation at Yield (50 mm/min)	9	%	ISO 527
Impact			
Charpy Impact Strenght (Notched, 23°C)	2.0	kJ/m ²	ISO 179
Izod Impact Strenght (Notched, 23°C)	2.5	kJ/m ²	ISO 180
Thermal			
Vicat Softening Temperature (10N)	154	°C	ISO 306
Heat Deflection Temperature (0.45 MPa)	90	°C	ISO 75B

Notes

These are typical property values not to be construed as specification limits

REACH

Polypropylene are exempted from registration under REACH. However, the corresponding monomers (used as raw materials for polymer production) and production) and relevant additives have been registered. Please see related Declaration of Compliance for Plastic Food Contact Materials (DoC for PFCM).

Packaging

Polypropylene pellets is typically packed in polyethylene bags with net weight of 25kg each. 50 bags are stacked on a flat wooden pallet (dimensions: 1100mm x 1300mm x 150mm) with net weight of 1250kg per pallet that is stretch-hood film wrapped. Upon agreement with a customer PP pellet can be packed into big bag sized for 1000kg on wooden pallet (dimensions: 1140mm x 1140mm x 150mm) without stretch-hood film wrapping.

Storage

Polypropylene product packed in 25kg bags or 1000kg big bags stacked on wooden pallet shall be stored in enclosed dry place preventing from direct sunlight at least 1 meter far from heaters, at temperature min. -15°C / max. 35°C, relative humidity max. 80%. Prior to processing PP product bags shall be kept in production area for at least 12 hours.

PP shelf life is 36 months from the date of manufacture.

POLYPROPYLENE HOMOPOLYMER