



SABIC® PP REX14077

PP random copolymer for Injection moulding

Description:

SABIC® PP REX14077 is a polypropylene random copolymer grade with medium melt flow intended for producing injection-moulded articles of high clarity. This product is formulated with an additive package, which enables a reduced cooling time in combination with high demoulding temperature. Products from SABIC® PP REX14077 have a very high clarity and a good impact strength-stiffness balance.

Health, Safety and Food Contact regulations:

Material Safety Data Sheets (MSDS) and Product Safety declarations are available on our Internet site <http://www.SABIC-europe.com>

The product mentioned herein is in particular not tested and therefore not validated for use in pharmaceutical/ medical applications.

Typical values

Revision 20140213

Properties	Unit (Si)	Values	Test methods
Polymer properties			
Melt flow rate (MFR) at 230 °C and 2.16 kg	dg/min	25	ISO 1133
Density	kg/m ³	905	ISO 1183
Formulation			
Anti static agent	-	Yes	-
Clarified	-	Yes	-
Mechanical properties			
Tensile test			ISO 527-2 1A
stress at yield	MPa	27	
strain at yield	%	14	
tensile modulus	MPa	1050	
Izod impact notched at 23 °C	kJ/m ²	5.0	ISO 180/1A
Charpy impact notched at 23 °C	kJ/m ²	6.0	ISO 179/1eA
Hardness Shore D	-	63	ISO 868
Thermal properties			
Heat deflection temperature at 1.80 MPa (HDT/A)	°C	50	ISO 75
at 0.45 MPa (HDT/B)	°C	75	
Vicat softening temperature at 10 N (VST/A)	°C	126	ISO 306
at 50 N (VST/B)	°C	68	



SABIC® PP REX14077 Provisional PP random copolymer for Injection moulding

Quality:

SABIC Europe is fully certified in accordance with the internationally accepted quality standard ISO9001.

Storage and handling:

Avoid prolonged storage in open sunlight, high temperatures (<50 °C) and /or high humidity as this could well speed up alteration and consequently loss of quality of the material and /or its packaging. Keep material completely dry for good processing.

Disclaimer. The information contained herein may include typical properties of our products or their typical performances when used in certain typical applications. Actual properties of our products, in particular when used in conjunction with any third party material(s) or for any non-typical applications, may differ from typical properties.

It is the customer's responsibility to inspect and test our product(s) in order to satisfy itself as to the suitability of the product(s) for its and its customers particular purposes. The customer is responsible for the appropriate, safe and legal use, processing and handling of all product(s) purchased from us.

Nothing herein is intended to be nor shall it constitute a warranty whatsoever, in particular, warranty of merchantability or fitness for a particular purpose.

SABIC Europe as referred to herein means any legal entity belonging to the SABIC Europe group of companies.