

Acran Boğaziçi Kimya A.Ş. Mahmutbey Mah. (İstoç Tic. Merk) 2412 Sk. (C Plaza) No:2



Luban RP2251R Polypropylene Random Copolymer



Description

Luban RP2251R is manufactured using the Spheripol Technology. Luban RP2251R is a clarified polypropylene random copolymer for producing injection molded & ISBM articles. Luban RP2251R offers good flowability, excellent transparency and superior aesthetic performance. Also contains antistatic agent that reduces static charge build-up on products.

Luban RP2251R can be processed at lower processing temperatures, allows reduction in energy consumption and improved productivity.

Applications

Transparent containers, housewares items, caps & closures, bottles (ISBM), and lids.

Properties (Typical Values)

Property	Units	Test method	Value
Melt flow rate (230°C/2.16 kg)	g/10 min	ISO 1133	25
Density	g /cm³	ISO 1183	0.90
Tensile modulus (1 mm/min)	MPa	ISO 527-2	1150
Tensile stress at yield (50 mm/min)	MPa	ISO 527-2	30
Tensile strain at yield (50 mm/min)	%	ISO 527-2	11
Tensile strain at break (50 mm/min)	%	ISO 527-2	> 50
Charpy notched impact strength (+23°C)	kJ/m²	ISO 179/1eA	6.0
Charpy notched impact strength (0°C)	kJ/m²	ISO 179/1eA	2
Heat Deflection Temperature (0.45 MPa)	°C	ISO 75-B	80
Haze, (1 mm - injection molded disc)	%	ASTM D1003	9
Vicat Softening Temperature (10N)	°C	ISO 306-A	130

Note: These are typical properties only and are not to be construed as specifications. Users should confirm results by their own tests.

Processing Guidlines

The Typical Processing Conditions for Luban RP2251R are:

Melt temperature	190 – 230 °C
Holding pressure	200 – 500 bar Maximum to avoid sink marks
Mold temperature	20 – 40 °C
Injection speed	High
Shrinkage	1 – 2 % depending on wall thickness and molding parameters

Note: Processing parameters should only be used as guidelines. The above properties values are not to be construed as specifications.

This document is classified as "Confidential" information, Please share this information on a "Need-to-Know" basis. أوكيو المكتب الرئيسي PO Box 281, PC 118 Muscet Grand Mall Muscet, Sultanate of Oman www.og.com



Acran Boğaziçi Kimya A.Ş. Mahmutbey Mah. (İstoç Tic. Merk) 2412 Sk. (C Plaza) No:2



🔇 0 (212) 659 94 37 İç Kapı No : 56,57,58 / Bağcılar İstanbul

🌐 www.**acran**.com.tr 🧕 info@**acran**.com.tr

Luban RP2251R **Polypropylene Random Copolymer**



Storage and Handling

Luban RP2251R must be protected from direct sunlight and should be stored in a shaded and completely dry area. During handling and processing, the material should be kept in a wellventilated area to prevent the accumulation of dust and fumes. Contact with strong oxidizers, excessive heat, sparks, or open flame should be avoided as this could initiate the degradation process and consequently impact the quality of the material.

Safety

Luban RP2251R is not classified as dangerous preparation. For further information about safety in handling and processing please refer to the Safety Data Sheet.

Food Contact

Luban RP2251R meets the requirements of the U.S. Food and Drug Administration (FDA) as specified in 21 CFR 177.1520, covering safe use of polyolefin articles and components of articles intended for direct food contact. For additional information on approved conditions of use for food contact applications, please refer to the "Product Stewardship Declaration."

Recycling

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

Updated: May 2024

Disclaimer:

Values given here are typical and should not be interpreted as specification. Before using OQ product, customers and other users should make their own independent determination that the product is suitable for the intended use. This document does not constitute a warranty, express or implied, including a warranty of merchantability or fitness for a particular purpose. In addition, no immunity under OQ or third parties' intellectual property rights shall be implied from this document. No one is authorized to make any warranties, issue any immunities or assume any liabilities on behalf of OQ except in a writing signed by an authorized OQ employee. Unless otherwise agreed in writing, the exclusive remedy for all claims is replacement of the product or refund of the purchase price at OQ's option, and in no event shall OQ be liable for special, consequential, incidental, punitive or exemplary damages.